

FEATURES

- High Clarity
- Easy to Process
- Practical Toughness
- FDA Rating: 21 CFR 177.1830
- USP Rating: Class VI Plastics
- Gamma & EtO Sterilizable

APPLICATIONS

- Glassware
- Cosmetic Packaging
- Appliances
- Medical Devices
- Office Supplies

PROPERTIES

| Physical | English | Value | Metric | Value | Test Method |
|--------------------------------------|--------------------|----------|-------------------|----------|-------------|
| Melt Flow Rate (200°C/5.0 Kg) | g/10 min | 7 | g/10 min | 7 | ASTM D1238 |
| Density | lb/ft ³ | 65 | g/cm ³ | 1.05 | ASTM D792 |
| Mechanical (*) | | | | | |
| Tensile Strength, Break | Kpsi | 3.2 | MPa | 22 | ASTM D638 |
| Break Elongation | % | 160 | % | 160 | ASTM D638 |
| Tensile Strength, Yield | Kpsi | 3 | MPa | 19 | ASTM D638 |
| Yield Elongation | % | 2 | % | 2 | ASTM D638 |
| Tensile Modulus | Kpsi | 222 | MPa | 1,530 | ASTM D638 |
| (*) 0.2 in/min (5 mm/min) | | | | | |
| Impact | | | | | |
| Notched Izod (0.125 in / 3.175 mm) | ft-lbf/in | 0.7 | J/m | 37 | ASTM D256 |
| Unnotched Izod (0.125 in / 3.175 mm) | ft-lbf/in | No Break | J/m | No Break | ASTM D256 |
| Thermal | | | | | |
| Vicat Temperature | °F | 194 | °C | 90 | ASTM D1525 |
| HDT @ 264 psi (Unannealed) | °F | 159 | °C | 70 | ASTM D648 |
| Optical | | | | | |
| Haze | % | 5 | % | 5 | ASTM D1003 |
| Light Transmittance | % | 87 | % | 87 | ASTM D1003 |

Properties reported in this data sheet are determined according to referred standard methods. Values shown represent averages from typical results measured in the laboratory and are provided only as a guide, not as specification limits.

INJECTION MOLDING CONDITIONS

| | °C | °F |
|---------------------|---------|---------|
| Rear | 170-180 | 340-360 |
| Center | 180-190 | 360-375 |
| Front | 200-210 | 390-410 |
| Maximum Recommended | 250 | 480 |

ADDITIONAL INFORMATION

This product presents a very low moisture absorption and it is a common practice to process it without pre-drying; however, if it has been exposed to high humidity or in direct contact with water, it is recommended to dry it for 3 to 4 hours at 122°F (50°C). Resirene's materials are biological and chemically inert. If possible recycling of final parts is recommended. If you require dispose it, follow indications established by government laws, related norms and the material safety data sheet.

Warning

Combustion of this material may cause hazardous fumes and gases that may be dangerous to health, especially in enclosed places. It should be noted that excessive heating or long residence times may cause degradation or yellowing.

Note:

The data contained herein is provided for information purposes only. By providing such information, Resirene, S.A de C.V. makes no guarantee and does not assume any liability with respect to the accuracy or completeness of such information and the results obtained with this product in any specific instance; and hereby expressly disclaims all implied warranties of merchantability or fitness to a particular purpose. Nothing contained herein shall be constructed as a license to use the products of Resirene, S.A. de C.V. in any manner that would infringe any patent.