

**FEATURES**

- High Viscosity
- Heat Resistance
- Mechanical Resistance
- FDA Rating: 21 CFR 177.1640

**APPLICATIONS**

- Foaming
- Sheet Extrusion
- Single Service Cutlery and Drinkware
- Blending with HIPS

**PROPERTIES**

	English	Value	Metric	Value	Test Method
<b>Physical</b>					
Melt Flow Rate (200°C/5.0 Kg)	g/10 min	1.8	g/10 min	1.8	ASTM D1238
Density	lb/ft <sup>3</sup>	65	g/cm <sup>3</sup>	1.04	ASTM D792
<b>Mechanical</b>					
Break Elongation	%	5	%	5	ASTM D638
Tensile Modulus	Kpsi	490	MPa	3,380	ASTM D638
<b>Thermal</b>					
Vicat Temperature	°F	207	°C	97	ASTM D1525
HDT @ 264 psi (unannealed)	°F	194	°C	90	ASTM D648
<b>Ignition Characteristics</b>					
Flammability	-	<a href="#">HB</a>	-	<a href="#">HB</a>	UL 94
<b>Optical</b>					
Light Transmittance	%	90	%	90	ASTM D1003

Properties reported in this data sheet are determined according to referred standard methods. Values shown represent averages from typical results measured in the laboratory and are provided only as a guide, not as specification limits.

**EXTRUSION CONDITIONS**

	°C	°F
Initial zone	40	104
Feeding zone	180-190	356-374
Transport zone	190-200	374-392
Compression zone	200-210	392-410
Pumping zone	210-220	410-428
Melt	250	482

**ADDITIONAL INFORMATION**
**Warning:**

Combustion of this material may cause hazardous fumes and gases that may be dangerous to health, especially in enclosed places. It should be noted that excessive heating or long residence time may cause degradation or yellowing.

**Note:**

The data contained herein is provided for information purposes only. By providing such information, Resirene S.A de C.V. makes no guarantee and does not assume any liability with respect to the accuracy or completeness of such information and the results obtained with this product in any specific instance; and hereby expressly disclaims all implied warranties of merchantability or fitness to a particular purpose. Nothing contained herein shall be construed as a license to use the products of Resirene, S.A. de C.V in any manner that would infringe any patent.