Resirene

TECHNICAL DATA SHEET

RESIRENE® HF 555

GENERAL PURPOSE POLYSTYRENE (GPPS)

FEATURES

- High Flow
- Easy to Process
- High Productivity
- Ideal for Thin Wall and Complex Parts
- FDA Rating: 21 CFR 177. 1640

APPLICATIONS

- Injection Molding
- Coextrusion
- Cutlery
- Toys

PROPERTIES

Physical	English	Value	Metric	Value	Test Method
Melt Flow Rate (200°C/5.0 Kg)	g/10 min	16	g/10 min	16	ASTM D1238
Density	lb/ft^3	65	g/cm^3	1.04	ASTM D792
Mechanical					
Break Elongation	%	3	%	3	ASTM D638
Tensile Strength, Break	Psi	5,500	MPa	38	ASTM D638
Tensile Modulus	Kpsi	525	MPa	3,620	ASTM D638
Thermal					
Vicat Temperature	°F	178	°C	81	ASTM D1525
HDT @ 264 psi (unannealed)	°F	165	°C	74	ASTM D648
Ignition Characteristics					
Flammability	-	HB	-	HB	UL 94
Optical					
Light Transmittance	%	90	%	90	ASTM D1003

Properties reported in this data sheet are determined according to referred standard methods. Values shown represent averages from typical results measured in the laboratory and are provided only as a guide, not as specification limits.

INJECTION MOLDING CONDITIONS

	°C	°F
Rear	190-200	375-390
Center	200-210	390-410
Front	210-220	410-430
Nozzle	220-230	430-445

ADDITIONAL INFORMATION

Warning:

Combustion of this material may cause hazardous fumes and gases that may be dangerous to health, especially in enclosed places.
It should be noted that excessive heating or long residence time may cause degradation or yellowing.

Note:
The data contained herein is provided for information purposes only. By providing such information, Resirene S.A de C.V. makes no guarantee and does not assume any liability with respect to the accuracy or completeness of such information and the results obtained with this product in any specific instance; and hereby expressly disclaims all implied warranties of merchantability or fitness to a particular purpose. Nothing contained herein shall be constructed as a license to use the products of Resirene, S.A. de C.V in any manner that would infringe any patent.

Carretera Fed. Puebla-Tlaxcala
Km. 15.5 • CP 90780
Xicohtzinco, Tlaxcala, México

MEX 01 800 RESINAS
USA 1 866 372 3470
www.resirene.com