

FEATURES

- High Flow
- Easy to Process
- High Productivity
- Ideal for Thin Wall and Complex Parts
- FDA Rating: 21 CFR 177.1640

APPLICATIONS

- Injection Molding
- Coextrusion
- Cutlery
- Toys

TYPICAL PROPERTY VALUES

Physical	English	Value	SI	Value	Test Method
Melt Flow Rate (200°C/5.0 Kg)	g/10 min	16	g/10 min	16	ASTM D1238
Density	lb/ft ³	65	g/cm ³	1.04	ASTM D792
Mechanical					
Break Elongation	%	1.4	%	1.4	ASTM D638
Tensile Strength, Break	psi	5,400	MPa	37	ASTM D638
Tensile Modulus	kpsi	424	MPa	2,925	ASTM D638
Thermal					
VICAT Softening Temperature (120°C/, 10 N)	°F	205	°C	96	ASTM D1525
Heat Deflection Temperature (264 psi, unannealed)	°F	163	°C	73	ASTM D648
Ignition Characteristics					
Flammability	-	HB	-	HB	UL 94
Optical					
Light Transmittance	%	90	%	90	ASTM D1003

Properties reported in this data sheet are determined according to referred standard methods. Values shown represent averages from typical results measured in the laboratory and are provided only as a guide, not as specification limits.

INJECTION MOLDING CONDITIONS

	°C	°F
Rear	190-200	375-390
Center	200-210	390-410
Front	210-220	410-430
Nozzle	220-230	430-445

ADDITIONAL INFORMATION

Warning

Combustion of this material may cause hazardous fumes and gases that may be dangerous to health, especially in enclosed places. It should be noted that excessive heating or long residence time may cause degradation.

Note: The data contained herein is provided for information purposes only. By providing such information, Resirene S.A de C.V. makes no guarantee and does not assume any liability concerning the accuracy or completeness of such information and the results obtained with this product in any specific instance; because of this, expressly disclaims all implied warranties of merchantability or fitness to a particular purpose. Nothing contained herein shall be constructed as a license to use the products of Resirene, S.A. de C.V in any manner that would infringe any patent.