

# TECHNICAL DATA SHEET

# RESIRENE® HH 103

## GENERAL PURPOSE POLYSTYRENE (GPPS)

### FEATURES

- High Viscosity
- Heat Resistance
- Mechanical Resistance
- Excellent Transparency
- FDA Rating: 21 CFR 177.1640

### APPLICATIONS

- Foaming
- Sheet Extrusion
- Single Service Cutlery and Drinkware
- Blending with HIPS

### PROPERTIES

Physical	English	Value	Metric	Value	Test Method
Melt Flow Rate (200°C/5.0 kg)	g/10 min	1.8	g/ 10 min	1.8	ASTM D1238
Density	lb/ft3	65	g/cm3	1.04	ASTM D792
Mechanical					
Break Elongation	%	3.0	%	3.0	ASTM D638
Tensile Strength, Break	Psi	7,000	MPa	48	ASTM D638
Tensile Modulus (* ) 0.2 in/min (5 mm/min)	Kpsi	433	MPa	2985	ASTM D638
Impact					
Notched Izod Impact (0.125mm)	ft-lb <sub>f</sub> /in	0.35	J/m	18.6	ASTM D256
Thermal					
Vicat	°F	225	°C	107	ASTM D1525
HDT @ 264 psi (unannealed)	°F	172	°C	78	ASTM D648
Características de Ignición					
Flamabilidad	-	<a href="#">HB</a>	-	<a href="#">HB</a>	UL 94
Optical					
Light Transmission	%	90	%	90	ASTM D1003

Properties reported in this data sheet are determined according to referred standard methods. The values shown represent averages from typical results measured in the laboratory and are provided only as a guide, not as specification limits.

### EXTRUSION CONDITIONS

	°C	°F
Initial Zone	40	104
Feeding zone	180-190	356-374
Transport zone	190-200	374-392
Compression zone	200-210	392-410
Pumping zone	210-220	410-428
Melt	230	446

### ADDITIONAL INFORMATION

#### Warning

Combustion of this material may cause hazardous fumes and gases that may be dangerous to health, especially in enclosed places. It should be noted that excessive heating or long residence time may cause degradation.

Note: The data contained herein is provided for information purposes only. By providing such information, Resirene S.A de C.V. makes no guarantee and does not assume any liability concerning the accuracy or completeness of such information and the results obtained with this product in any specific instance; because of this, expressly disclaims all implied warranties of merchantability or fitness to a particular purpose. Nothing contained herein shall be constructed as a license to use the products of Resirene, S.A. de C.V in any manner that would infringe any patent.