

### FEATURES

- Medium Flow
- Heat Resistance
- Good Mold Release
- FDA Rating: 21 CFR 177.1640

### APPLICATIONS

- Injection Molding
- Pen Barrels
- Disposable Items
- Scholar and Office Supplies

### TYPICAL PROPERTY VALUES

Physical	English	Value	SI	Value	Test Method
Melt Flow Rate (200°C/5.0 kg)	g/10 min	4	g/ 10 min	4	ASTM D1238
Density	lb/ft <sup>3</sup>	65	g/cm <sup>3</sup>	1.04	ASTM D792
Mold Shrinkage	%	0.3 – 0.7	%	0.3 – 0.7	ASTM D 955
Mechanical					
Break Elongation	%	2.1	%	2.1	ASTM D638
Tensile Strength, Break	psi	6,900	MPa	48	ASTM D638
Tensile Modulus	kpsi	447	MPa	3,080	ASTM D638
Thermal					
VICAT Softening Temperature (120°C/, 10 N)	°F	228	°C	109	ASTM D1525
Heat Deflection Temperature (264 psi unannealed)	°F	174	°C	79	ASTM D648
Ignition Characteristics					
Flammability	-	<a href="#">HB</a>	-	<a href="#">HB</a>	UL 94
Optical					
Light Transmission	%	90	%	90	ASTM D1003

Properties reported in this data sheet are determined according to referred standard methods. Values shown represent averages from typical results measured in the laboratory and are provided only as a guide, not as specification limits.

### INJECTION CONDITIONS

	°C	°F
Initial Zone	40	104
Feeding zone	180-190	356-374
Transport zone	190-200	374-392
Compression zone	200-210	392-410
Pumping zone	210-220	410-428
Melt	230	446

### ADDITIONAL INFORMATION

#### Warning

Combustion of this material may cause hazardous fumes and gases that may be dangerous to health, especially in enclosed places. It should be noted that excessive heating or long residence time may cause degradation.

Note: The data contained herein is provided for information purposes only. By providing such information, Resirene S.A de C.V. makes no guarantee and does not assume any liability concerning the accuracy or completeness of such information and the results obtained with this product in any specific instance; because of this, expressly disclaims all implied warranties of merchantability or fitness to a particular purpose. Nothing contained herein shall be constructed as a license to use the products of Resirene, S.A. de C.V in any manner that would infringe any patent.